

HyperBOND

100% SOLIDS EPOXY BASECOAT

PRODUCT OVERVIEW

HyperBOND is an incredible 100% solids, water-insensitive epoxy resin exhibits superior bonding characteristics, and can be installed over damp concrete as it boasts outstanding water-insensitivity technology. Just get rid of any standing puddles and you are ready to install. Use HyperBOND to install beautiful, seamless, and durable floors that are easy to clean. This self-priming epoxy features a buttery smooth viscosity and can withstand up to 9 lbs. of moisture vapor emissions. HyperBOND is ideal for wherever a high-build, protective coating is required. Perfect anywhere an epoxy base coat is recommended and is ideal for humid climates where concrete sweating occurs. HyperBOND can be used in residential, commercial, and industrial applications. Available in clear, 6 standard colors or can be field pigmented using E-POLY universal pigment packs.

KEY FEATURES

- Low VOC Formulation
- Low Odor
- Moisture Insensitive
- Excellent Adhesion
- Reduced Humidity Sensitivity
- Chemical Resistance
- Abrasion Resistance
- Enhanced Durability
- High Compressive Strength
- Broadcast Compatible

COLOR OPTIONS



APPLICATION CONSIDERATIONS

- Colors or gloss may be affected by high humidity, low temperatures, chemical exposure, or exposure to spectrum wavelength lighting and UV
- Slab on grade requires moisture barrier
- Will not bridge substrate cracking
- Colors may vary from batch to batch, therefore use only product from the same batch for an entire job or box all pigment components prior

PHYSICAL CHARACTERISTICS

SOLIDS CONTENT	100%
VOLUMETRIC MIX RATIO	2A:1B
VISCOSITY	2,000 cps
POT LIFE 1.5 GAL MASS	30-40 Minutes @ 75°F
WORKING TIME	35-45 Minutes @ 70°F
TACK FREE	8-12 Hours @ 75°F
RECOAT WINDOW	8-24 Hours @ 75°F
LIGHT FOOT TRAFFIC	24 Hours @ 75°F
FULL CURE	5 Days
APPLICATION TEMPERATURE	45°F - 90°F RH <85%
COVERAGE RATE	80-160 ft ² /gal @ 10-20 Mils WFT
SHELF LIFE UNOPENED	1 Year
PACKAGING	3 Gallon Kit 15 Gallon Kit

TECHNICAL PROPERTIES

HARDNESS	ASTM D2240	Shore D 82
COMPRESSIVE STRENGTH	ASTM D695	12,300 psi
TENSILE STRENGTH	ASTM D638	9,300 psi
FLEXURAL STRENGTH	ASTM D790	10,465 psi
GLOSS INDEX @ 60°	ASTM D112	60-90
ADHESION	ASTM D7234	450 psi Concrete Failure
ABRASION RESISTANCE CS-17 WHEEL, 1000G LOAD, 500 CYCLES	ASTM D4060	36 mg loss
IMPACT RESISTANCE DIRECT & REVERSE 50 IN/LBS	ASTM D5420	PASS

CHEMICAL RESISTANCE

Refer to Floorguard Products Chemical Resistance Chart.

☰ REQUIREMENTS

- The substrate should have a compressive strength of at least 3,500 psi
- The substrate should have a Moisture Vapor Emission Rate (MVER) of less than 9 lbs per ASTM F1869 and a Relative Humidity (RH) below 80% per ASTM F2170. When using a Tramex concrete moisture meter, the moisture content should be under 4%
- The substrate should have a pH level in the range of 6 to 9.
- Concrete must be structurally sound and free of all contaminants and bond breakers.
- Concrete should be mechanically prepared and profiled to achieve a Concrete Surface Profile (CSP) between levels 2 and 4, in accordance with ICRI 310.2R
- Mask all perimeter areas to protect surfaces at coating terminations. Saw-cut and key all termination points as required.
- Ensure all depressions, divots, and cracks are properly profiled, cleaned of dust and contaminants, and repaired to prevent defects from showing through the coating.
- Preserve all dynamic joints, while static joints can be filled. When necessary, use dynamic joints as starting and ending points during the application process.
- Ambient and substrate temps should be above 50°F and a minimum of 5°F above Dew Point.
- Product temps should be between 70-80°F.
- Ambient relative humidity should not exceed 80% during coating application.

⚠ PRECAUTIONS

- Refer to Safety Data Sheets (SDS) for safety precautions.
- Safety precautions must be followed during storage, handling, and use.
- Personal Protective Equipment (PPE) shall be worn at all times of the application process including but not limited to long sleeve shirts, safety glasses, nitrile gloves and properly fitted NIOSH respirators.
- All sources of ignition must be turned off, and the area should be properly and adequately ventilated during both the application and curing processes.
- The mixing area should be located on or near the project site and securely covered with plastic, cardboard, or a tarp to protect against drips and spills.
- Stage all materials, tools, and cleaning supplies in a shaded area—out of direct sunlight—within the mixing area before beginning the application process.
- Clean the mixing station and application tools after use with a VOC-exempt solvent. Always follow all legal, health, and safety guidelines when handling or storing solvents and materials, especially when working in confined spaces.
- Dispose of empty packaging and other waste in accordance with all applicable federal, state, provincial, and local regulations.

☰ MIXING PROCEDURE

1. Pre condition product to temperature between 70°-80°F for best results
2. Pre-Mix A-Component in its respective container using Jiffy mixer and drill at slow speeds for 30 seconds until thoroughly homogeneous
 - If field pigmenting clear using E-Poly Universal Colorants, add 8 oz pigment per gal (dark colors) or 10-12 oz pigment per gal (light colors) to A-Component and mix until color is uniform.
3. Pre-Mix B-Component in its respective container using clean Jiffy mixer and drill at slow speeds for 30 seconds or until thoroughly homogeneous.
4. Transfer A-component and B-component at a mix rate of 2A:1B by volume and mix for 2-3 minutes being sure to scrape sides of the bucket ensuring both components are thoroughly blended
 - Do not mix at high RPMs or air entrapment may occur
 - Do not pull mixing paddle in and out of the mix during process or air entrapment may occur

☰ COVERAGE RATES & WORKING TIMES

<ul style="list-style-type: none">• Basecoat: 160 Ft² / Gal @ 10 Mils WFT• Buildcoat: 80 Ft² / Gal @ 20 Mils WFT	<ul style="list-style-type: none">• 45-60 Minute Working Time @ 52°F• 35-45 Minute Working Time @ 70°F• 20-30 Minute Working Time @ 88°F
<ul style="list-style-type: none">• Surface porosity, temperatures, and application method will cause coverage rate to vary.• Ambient temps & humidity, product and surface temps, airflow and mix time affect overall working times	

☰ APPLICATION PROCEDURE

1. Cut-in edges using a chip brush. Do not allow wet edges to stand more than 5 minutes ahead of application of main body of floor.
 - Epoxy sets faster in mass; Mixed material should not remain in bucket
 - Be mindful of environmental variables and affects on estimated working time
2. Pour mixed material across the surface. Use 8-12 or 15-20 mil notched squeegee to gauge material across surface achieving desired thickness.
 - Do not flip bucket upside down and allow to sit on surface
 - Ensure you maintain a wet edge throughout application process
 - Follow recommended coverage rates and wet film thickness
3. Pre-wet 18" x 3/8" nap roller and back roll the surface wall to wall with 50% overlap. Back roll should be perpendicular to your first pass.
 - Do not overwork material
 - Ensure back roll is always either wall to wall or joint to joint for a consistent finish
4. Allow coating to dry : 16-30 Hours @ 57°F
 - 8-12 Hours @ 75°F
 - 4-6 Hours @ 93°F
 - Do not force dry
 - Recoat: 8-24 Hours @ 75°F
- If coating has no broadcast aggregate, surface will need to be abraded using 80-100 sanding screen prior to recoat after the 24 hour window
 - Light Traffic: 24 Hours @ 75°F
 - Heavy Traffic: 48 Hours @ 75°F
 - Equipment Traffic: 72 Hours @ 75°F
- Lower temps will further delay traffic time

☰ MAINTENANCE

Inspect the installed floor by spot-cleaning and repairing any damaged or cracked areas as needed. To extend the life of the flooring system, implementing a daily maintenance program is strongly recommended to help ensure the floor remains safe for its intended use.

☰ TECHNICAL SUPPORT

For questions, please contact a Floorguard Products representative. Additional support materials are available from Floorguard Products. Visit floorguardproducts.com or reach out to us directly for further resources.

⚠ DISCLAIMER

All guidelines, recommendations, statements, and technical data in this document are based on information and testing believed to be accurate and reliable. However, their accuracy or completeness is not guaranteed, and nothing herein should be construed as an expressed or implied warranty. Users are responsible for conducting their own evaluations and testing to determine the suitability of the product for their specific use, application, and job conditions, and assume all associated risks and liabilities. We do not imply that any stated product limitations are the only ones that may exist. Neither the Seller nor the Manufacturer shall be liable for any direct or indirect injury, loss, or damage resulting from the use of, or inability to use, the products. Any recommendations or statements not included in this document are not binding on the Manufacturer. Technical and application information is provided to give a general understanding of the material and proper application methods. Test results were obtained under controlled conditions, and the Manufacturer does not claim these results represent all possible environments. The Manufacturer is not responsible for typographical errors.