

ZioTHANE

GLOSS WB URETHANE

PRODUCT OVERVIEW

ZioTHANE is a high-performance, two-component, water-based aliphatic urethane sealer designed to deliver a durable, gloss finish for concrete floors. Formulated with advanced urethane technology, ZioTHANE provides exceptional resistance to abrasion, chemicals, and UV exposure, making it ideal for both commercial and residential environments. This eco-friendly, low-odor system offers excellent clarity and gloss retention, enhancing the appearance of decorative coatings. ZioTHANE creates a long-lasting, easy-to-clean surface that stands up to daily wear while maintaining a brilliant, gloss finish.

KEY FEATURES

- Low VOC Formulation
- Low Odor
- Eco-Friendly
- Breathable Film
- UV Stability
- Excellent Gloss Stability
- Chemical & Impact Resistance
- Excellent Abrasion Resistance
- Slip-Resistance Options
- Low Maintenance

COLOR OPTIONS



CLEAR

APPLICATION CONSIDERATIONS

- Higher ambient, product, and substrate temps will decrease working time and dry time
- Slab on grade requires moisture barrier
- Do not thin
- Do not apply heavier than recommended coverage rate

PHYSICAL CHARACTERISTICS

SOLIDS CONTENT	43%
VOC CONTENT	10 g/L
VOLUMETRIC MIX RATIO	2A:1B
VISCOSITY	500-1,000 cps
POT LIFE 1.5 GAL MASS	60 Minutes @ 70°F
WORKING TIME	35-45 Minutes @ 70°F
TACK FREE	7-9 Hours @ 70°F
RECOAT WINDOW	7-12 Hours @ 75°F
LIGHT FOOT TRAFFIC	24 Hours @ 75°F
FULL CURE	3-5 Days
APPLICATION TEMPERATURE	55°F - 90°F RH <85%
COVERAGE RATE	350 ft ² /gal @ 4.5 Mils WFT
SHELF LIFE UNOPENED	6 Months
PACKAGING	3 Gallon Kit 15 Gallon Kit

TECHNICAL PROPERTIES

ABRASION RESISTANCE CS-17 WHEEL, 1000G LOAD, 500 CYCLES	ASTM D4060	21 mg loss
ADHESION	ASTM D7234	>320 psi
FLEXIBILITY 1/8" MANDREL	ASTM D1737	Pass
GLOSS INDEX @ 60°	ASTM D112	>70
IMPACT RESISTANCE	ASTM D2794	121 lbs/in

CHEMICAL RESISTANCE

Refer to Floorguard Products Chemical Resistance Chart.

REQUIREMENTS

- The substrate should have a compressive strength of at least 3,500 psi
- The substrate should have a Moisture Vapor Emission Rate (MVER) of less than 3 lbs per ASTM F1869 and a Relative Humidity (RH) below 80% per ASTM F2170. When using a Tramex concrete moisture meter, the moisture content should be under 4%
- The substrate should have a pH level in the range of 6 to 9.
- Concrete must be structurally sound and free of all contaminants and bond breakers.
- Concrete should be mechanically prepared and profiled to achieve a Concrete Surface Profile (CSP) between levels 2 and 4, in accordance with ICRI 310.2R
- Mask all perimeter areas to protect surfaces at coating terminations. Saw-cut and key all termination points as required.
- Ensure all depressions, divots, and cracks are properly profiled, cleaned of dust and contaminants, and repaired to prevent defects from showing through the coating.
- Preserve all dynamic joints, while static joints can be filled. When necessary, use dynamic joints as starting and ending points during the application process.
- Ambient and substrate temps should be above 55°F and a minimum of 5°F above Dew Point.
- Product temps should be between 70-80°F.
- Ambient relative humidity should not exceed 80% during coating application.

PRECAUTIONS

- Refer to Safety Data Sheets (SDS) for safety precautions.
- Safety precautions must be followed during storage, handling, and use.
- Personal Protective Equipment (PPE) shall be worn at all times of the application process including but not limited to long sleeve shirts, safety glasses, nitrile gloves and properly fitted NIOSH respirators.
- All sources of ignition must be turned off, and the area should be properly and adequately ventilated during both the application and curing processes.
- The mixing area should be located on or near the project site and securely covered with plastic, cardboard, or a tarp to protect against drips and spills.
- Stage all materials, tools, and cleaning supplies in a shaded area—out of direct sunlight—within the mixing area before beginning the application process.
- Clean the mixing station and application tools after use with a VOC-exempt solvent. Always follow all legal, health, and safety guidelines when handling or storing solvents and materials, especially when working in confined spaces.
- Dispose of empty packaging and other waste in accordance with all applicable federal, state, provincial, and local regulations.

MIXING PROCEDURE

1. Pre condition product to temperature between 70°-80°F for best results
2. Pre-Mix A-Component in its respective container using Jiffy mixer and drill at slow speeds for 30 seconds until thoroughly homogeneous
3. Pre-Mix B-Component in its respective container using clean Jiffy mixer and drill at slow speeds for 30 seconds or until thoroughly homogeneous.
4. Transfer A-component and B-component at a mix rate of 2A:1B by volume and mix for 2-3 minutes being sure to scrape sides of the bucket ensuring both components are thoroughly blended
 - Do not mix at high RPMs or air entrapment may occur
 - Do not pull mixing paddle in and out of the mix during process or air entrapment may occur

COVERAGE RATES & WORKING TIMES

- Sealer: 350 Ft² / Gal @ 4.5 Mils WFT
 - 45-50 Minute Working Time @ 55°F
 - 30-45 Minute Working Time @ 70°F
 - 20-30 Minute Working Time @ 88°F

- Surface porosity, temperatures, and application method will cause coverage rate to vary.
- Ambient temps & humidity, product and surface temps, airflow and mix time affect overall working times

APPLICATION PROCEDURE

1. Cut-in edges using a chip brush. Do not allow wet edges to stand more than 5 minutes ahead of application of main body of floor.
2. Pour mixed material into paint tray and use a 1/4" nap mohair roller to dip and roll material across surface achieving desired thickness.
3. Back roll the surface wall to wall with 50% overlap. Back roll should be perpendicular to your first pass
 - Do not overwork material
 - Ensure back roll is always either wall to wall or joint to joint for a consistent finish
4. Allow coating to dry : 10-14 Hours @ 52°F
 - 7-9 Hours @ 70°F
 - 4-6 Hours @ 88°F
 - Do not force dry
 - Recoat: 7-12 Hours @ 75°F
- Surface will need to be abraded using 80-100 sanding screen prior to recoat after the 12 hour window
 - Light Traffic: 24 Hours @ 75°F
 - Heavy Traffic: 48 Hours @ 75°F
 - Equipment Traffic: 72 Hours @ 75°F
- Lower temps will further delay traffic time

MAINTENANCE

Inspect the installed floor by spot-cleaning and repairing any damaged or cracked areas as needed. To extend the life of the flooring system, implementing a daily maintenance program is strongly recommended to help ensure the floor remains safe for its intended use.

TECHNICAL SUPPORT

For questions, please contact a Flooguard Products representative. Additional support materials are available from Flooguard Products. Visit flooguardproducts.com or reach out to us directly for further resources.

DISCLAIMER

All guidelines, recommendations, statements, and technical data in this document are based on information and testing believed to be accurate and reliable. However, their accuracy or completeness is not guaranteed, and nothing herein should be construed as an expressed or implied warranty. Users are responsible for conducting their own evaluations and testing to determine the suitability of the product for their specific use, application, and job conditions, and assume all associated risks and liabilities. We do not imply that any stated product limitations are the only ones that may exist. Neither the Seller nor the Manufacturer shall be liable for any direct or indirect injury, loss, or damage resulting from the use of, or inability to use, the products. Any recommendations or statements not included in this document are not binding on the Manufacturer. Technical and application information is provided to give a general understanding of the material and proper application methods. Test results were obtained under controlled conditions, and the Manufacturer does not claim these results represent all possible environments. The Manufacturer is not responsible for typographical errors.